



International Fireproof Technology Inc.

The Ultimate In Fire Protective Coatings and Flame Retardant Products

Paint to Protect™
949.975.8588



Approved Foam Testing Matrix For DC315

Building Code Fire Performance Requirements for SPF: The International Building Code (IBC) mandates that SPF be separated from the interior of the building by a prescriptive 15-minute thermal barrier, or other approved covering. DC315 Carries IAPMO ER-0499 and ICC-ESR 3702 Evaluation Reports confirming DC315 provides an alternative thermal barrier assembly to the prescriptive thermal barrier requirements and all testing complies with the 2012 IBC Section 803.1.2 & 2603.10. 2012 IRC Section 316.6. 2015 IBC Section 803.2.1, 803.11, 2603.9 and 2015 IRC Section 316.6. DC 315 has also been tested as an ignition barrier under AC 377 Appendix X and meets the requirements of ICC-ES AC377 and AC456 Criteria.

Light Gold Cells are Ignition Barrier Light Green Cells are Thermal Barrier

Approved (SPF) Spray Foam Manufacturer and Type	Wet Film	Dry Film	Coverage Rate Per Gallon	IFTI ICC-ESR Evaluation report	IFTI IAPMO Evaluation report	SPF Manufacturer Evaluation report
Accella Bayseal CCX 2 lb.	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0522
Accella Bayseal CCXP 2 lb.	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0522
Accella Bayseal OC 0.5 lb.	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0519
Accella Bayseal OC 0.5 lb.	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0519
Accella Bayseal OCX 0.5 lb.	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0541
Accella Ecobay CC 2 lb.	18	12	89 sq.ft.	ESR-3702	ER-0499	ER-0520
Accella Ecobay Polar 2 lb. CC	18	12	89 sq.ft.	ESR-3702	ER-0499	ER-0520
Accella Foamsulate 210 2 lb. CC	20	13	80 sq.ft.	ESR-3702	ER-0499	ER-0351
Accella Foamsulate 220 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0352
Accella Foamsulate 50 0.5 lb. OC	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0351
Accella Foamsulate 50 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0351
Accella Foamsulate 50-HY 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ES-0540
Accella Foamsulate 50-NIB 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0394
Accella NatureSeal @ 500	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0285

Approved (SPF) Spray Foam Manufacturer and Type	Wet Film	Dry Film	Coverage Rate Per Gallon	IFTI ICC-ESR Evaluation report	IFTI IAPMO Evaluation report	SPF Manufacturer Evaluation report
Accella QuadFoam® 2.0 lb. CC	14	9	New Spread Rate 115 sq.ft	ESR-3702	ER-0499	ER-0272
Accella QuadFoam® 500 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft	ESR-3702	ER-0499	ER-0271
Accella QuadFoam® 500 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0271
Accella QuadFoam® NeXGen HFO 2 lb. CC	18	12	89 sq.ft.	ESR-3702	ER-0499	ER-0523
Accella Sealtite 0.7lb OC+	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0557
Accella Sealtite 0.7lb OC+	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0557
Accella Sealtite 2lb CC+	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0556
BASF 158 SPRAYTITE ® 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-2642
BASF 158 SPRAYTITE® 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-2642
BASF ENERTITE ® NM 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3102
BASF ENERTITE ® NM 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-3102
BASF ENERTITE® G OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3102
BASF ENERTITE® G OC	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR-3102
BASF LWP-H	14	9	115 sq. ft.	Update in Progress	Update in Progress	CCRR-1031
BASF Spraytite 81205	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR 2642
BASF Spraytite 81206	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR 2642
BASF Spraytite SP	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR 2642
BASF SPRAYTITE ® 81206 2 lb. cc	20	14	80 sq. ft.	ESR-3702	ER-0499	ESR-2642
BASF SPRAYTITE® 178 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-2642
BASF SPRAYTITE® 178 2 lb. CC	20	14	80 sq. ft.	ESR-3702	ER-0499	ESR-2642
BASF SPRAYTITE® 81205 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-2642
BASF SPRAYTITE® SP 2 lb. CC	14	9	New Spread Rate 115 sq.ft	ESR-3702	ER-0499	ESR-2642
BASF WALLTITE 200 CC	20	14	80 sq. ft	Update in Progress	ER-0499	ESR-2642
BASF WALLTITE 200 CC	4	3	400 sq. ft.	Update in Progress	ER-0499	ESR-2642
BASF Walltite HP+	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR 2642
BASF Walltite US	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR 2642
BASF Walltite US-N	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR 2642
BASF WALLTITE® HP+ 2 lb. CC	20	14	80 sq. ft.	ESR-3702	ER-0499	ESR-2642
BASF WALLTITE® US 2 lb. CC	20	14	80 sq. ft.	ESR-3702	ER-0499	ESR-2642
BASF WALLTITE® US-N 2 lb. CC	20	14	80 sq. ft.	ESR-3702	ER-0499	ESR-2642
Caplon Systems Capthane 0.5	21	14	73 sq.ft.	Update in Progress	Update in Progress	ER-0574
Caplon Systems Capthane 1.6	4	3	400 sq. ft.	Update in Progress	Update in Progress	ER-576
Carlisle Foamsulate 50	4	3	400 sq. ft.	ESR-3702	ER-0499	ER-351
Carlisle Foamsulate 70	4	3	400 sq. ft.	ESR-3702	ER-0499	ER-627
Carlisle Sealtite Pro	4	3	400 sq. ft.	ESR-3702	ER-0499	ER-624
Carlisle Sealtite Pro No Mix	4	3	400 sq. ft.	ESR-3702	ER-0499	ER-616
Carlisle Sealtite Pro No Trim 21	4	3	400 sq. ft.	ESR-3702	ER-0499	ER-618
Certaiteed CertaSpray 2 lb. CC	4	3	400 sq.ft.	ESR-3702		ESR-3758
Certaiteed CertaSpray 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3758
CertainTeed CertaSpray X 0.5 lb OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3759
Creative Polymer Solutions Air Lok 170	4	3	400 sq. ft.	ESR-3702	Update in Progress	
Creative Polymer Solutions Air Lok 170	19	13	New Spread Rate 115 sq. ft	ESR-3702	Update in Progress	
Creative Polymer Solutions AirLok 45	4	3	400 sq. ft.	ESR-3702	ER-0499	ER-0554
Creative Polymer Solutions AirLok 45	18	12	89 sq. ft.	ESR-3702	ER-0499	ER-0554
DAP Touch N Foam Professional Class 1 FR 2 lb. CC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3052
DAP Touch N Seal Class 1 FR 2 lb. CC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3052
Demilec Agribalance 0.7 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-2600
Demilec Agribalance 0.7 lb. OC	18	12	89 sq.ft.	ESR-3702	ER-0499	ESR-2600
Demilec APX 0.5 lb. OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3470
Demilec APX 2.0	20	13	80	ESR-3702	Update in Progress	ESR-3703
Demilec Heatlok Arctic XT-w 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3883
Demilec Heatlok ECO	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR-3198
Demilec Heatlok ECO	22	14	73 sq. ft.	ESR-3702	Update in Progress	ESR-3198

Approved (SPF) Spray Foam Manufacturer and Type	Wet Film	Dry Film	Coverage Rate Per Gallon	IFTI ICC-ESR Evaluation report	IFTI IAPMO Evaluation report	SPF Manufacturer Evaluation report
Demilec Heatlok HFO High Lift 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-4073
Demilec Heatlok HFO High Lift 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-4073
Demilec Heatlok Soy 200+ 2 lb. CC	18	12	89 sq.ft.	ESR-3702	ER-0499	ESR-3210
Demilec Heatlok XT-s 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3824
Demilec Heatlok® HFO PRO 2 lb. CC	18	12	89 sq.ft.	ESR-3702	ER-0499	ER-0565
Demilec Sealection 500 0.5 lb. OC	18	12	89 sq.ft.	ESR-3702	ER-0499	ESR-1172
Demilec Sealection 500 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-1172
Demilec Sealection NM 0.5 lb. OC	18	12	89 sq. ft.	ESR-3702	ER-0499	ESR-2668
Diamondback Closed Cell Spray Foam	18	12	89 sq. ft.	Update in Progress	Update in Progress	ESR-4438
Dow FROTH-PAK1.75 lb. CC	20	13	80 sq.ft.	Update in Progress	ER-0499	ESR-3228
DOW Styrofoam CM 2045 2 lb. CC	22	14	73 sq. ft.	ESR-3702	ER-0499	ESR-2670
Elastochem Insulthane Extreme 2 lb.CC	18	12	89 sq.ft.	ESR-3702	ER-0499	ESR-3809
Energy One America EOA 2000 2 lb. CC	4	3	400 sq.ft.	Update in Progress	ER-0499	ER-0443
Energy One America EOA 2000 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0443
EnergyOne America EOA 500 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3686
Foamsulate 50	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0351
Foamsulate 50 HY	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0540
Foamsulate 70	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0627
Foamsulate Closed Cell	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0626
Foamsulate HFO	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0650
Foamsulate OCX	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0394
Gaco 052N 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	CCRR-1075
Gaco 052N 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCRR-1075
GACO EZ Spray F4500 0.5 OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCRR-1107
GACO EZ Spray F4500 0.5 OC	4	3	400 sq.ft.	ESR-3702	ER-0499	CCRR-1107
Gaco FireStop2 5001 0.5 lb. OC	18	12	89 sq.ft.	ESR-3702	ER-0499	CCRR-1009
Gaco OnePass F1850 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCRR-1043
Gaco Tough Foam 10 lb. CC	20	13	80 sq.ft.			
Gaco Western 183M 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCRR-1002
Gaco Western F1880 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCRR-1106
General Coatings Ultra-Thane 050 0.5 OC	20	13	80 sq.ft.	ESR-3702		
General Coatings Ultra-Thane 050 0.5 OC	4	3	400 sq.ft.	ESR-3702		
General Coatings Ultra-Thane 230 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	CCRR-1085
General Coatings Ultra-Thane 230 2 lb. CC	22	15	73 sq. ft.	ESR-3702	ER-0499	CCRR-1085
Guardian Energy Technologies Foam It Green 2 lb. CC	20	13	80 sq.ft.	ESR-3702	Update in Progress	
HandiFoam HVLP LD 0.5	18	12	89 sq. ft.	Update in Progress	Update in Progress	CCRR 1124
HandiFoam HVLP LD 0.5	4	3	400 sq. ft.	Update in Progress	Update in Progress	CCRR 1124
Henry Permax 2.0 X Fast CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3647
Henry Permax 2.0 X lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ERS-3647
Henry Permax LV 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-3646
Henry Permax RT 2045 2.0 CC	21	14	80 sq.ft.	ESR-3702	ER-0499	ESR-3024
Henry Permax RT-2045 1.8 lb. CC	21	14	80 sq.ft.	ESR-3702	ER-0499	ESR-3024
Hi-R OC	14	9	New Spread Rate 115 sq. ft	Update in Progress	ER-0499	ER-0675
ICP Adhesives & Sealants formerly Fomo Products Inc. Handi-Foam E84 Class 1 (A) 2 lb. CC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-2717
Icyene Classic Ultra Select 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-1826
Icyene Classic 0.5 lb OC	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR-1826
Icyene Classic Plus 0.7 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-1826
Icyene Classic Plus 0.7 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-1826

Approved (SPF) Spray Foam Manufacturer and Type	Wet Film	Dry Film	Coverage Rate Per Gallon	IFTI ICC-ESR Evaluation report	IFTI IAPMO Evaluation report	SPF Manufacturer Evaluation report
Icynene Classic Ultra 0.5 lb. OC	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ESR-1826
Icynene Classic Ultra 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-1826
Icynene Classic Ultra Select 0.5 lb. OC	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ESR-1826
Icynene Classic® 0.5 lb. OC	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ESR-1826
Icynene MD-C-200 2 lb. CC	22	14	73 sq.ft.	ESR-3702	ER-0499	ESR-3199
Icynene MDC-200 2.0 lb CC	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR-3199
Icynene OC No-Mix	14	9	New Spread Rate 115 sq. ft.	Update in Progress	Update in Progress	CCR-1123
Icynene OC No-Mix	4	3	400 sq. ft.	Update in Progress	Update in Progress	CCR-1123
Icynene ProSeal 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3500
Icynene ProSeal 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-3500
Icynene ProSeal HFO and HFO CW	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	CCR-1108
Icynene ProSeal LE	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR-3500
Icynene ProSeal LE CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3500
Icynene-Lapolla Prime Gold	4	3	400 sq. ft.	ESR-3702	Update in Progress	ESR-4323
Icynene-Lapolla Prime Gold	14	9	New Spread Rate 115 sq. ft.	ESR-3702	Update in Progress	ESR-4323
JM Corbond III 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0146
JM Corbond III 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0146
JM Corbond MCST™	22	14	73 sq.ft.	ESR-3702	ER-0499	ESR-3159
JM ocx SPF™	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0372
Lapolla FL 2000 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-2629
Lapolla FL 2000 4-G 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCR-1025
Lapolla FL 450 OC	4	3	400 sq. ft.	ESR-3702	ER-0499	ESR-4242
Lapolla FL 450 OC	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ESR-4242
Lapolla FL 500 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCR-1091
Lapolla FL 500 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	CCR-1091
Lapolla FL 750	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ESR-4322
Lapolla Foam-Lok AB2000 2.0 lb. CC	14	9	115 sq. ft.			ERS-2629
Natural Polymers Natural-Therm Light 0.5 OC	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ER-0589
Natural Polymers, Natural-Therm® 0.5 IB, OC	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0503
Natural Polymers, Natural-Therm® 0.5 OC	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0336
Natural Polymers, Natural-Therm® 2.0 IBS	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0336
Natural Polymers, Natural-Therm® 2.0 IBW	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0336
Natural Polymers, Natural-Therm® Zero CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0527
Natural Polymers,Natural-Therm® HFO 2 lb. CC	4	3	400 sq.ft.	ESR-3702		
Natural Polymers,Natural-Therm® ZERO 2 lb. CC	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0527
NCFI 12-008 0.5 lb. No Mix OC	14	9	New Spread Rate 115 sq. ft.	ESR-3702		UEL-5022
NCFI INSULBLOC® 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-1615
NCFI INSULSTAR® 1.7 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0667
NCFI INSULSTAR® 2 lb. CC	14	9	New Spread Rate 115 sq. ft.	ESR-3702	ER-0499	ESR-1615
NCFI SEALITE 0.5 lb. OCX	5	3	320 sq.ft.	ESR-3702		ESR-3826
NCFI SEALITE 0.5 lb. OCX	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3826
NuWool, Nu-Seal 0.5	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0504
NuWool, Nu-Seal 2.0 IBS and IBW	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0504
Patriot 200 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-4065
Patriot 200 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-4065

Approved (SPF) Spray Foam Manufacturer and Type	Wet Film	Dry Film	Coverage Rate Per Gallon	IFTI ICC-ESR Evaluation report	IFTI IAPMO Evaluation report	SPF Manufacturer Evaluation report
Patriot 500 0.5 lb. OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-4064
Patriot 500 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-4064
Patriot 500 HY 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-4064
Patriot 500 HY 0.5 lb. OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-4064
Polygreen GreenSeal 44	4	3	400 sq. ft.	ESR-3702		ER-0606
Polygreen Solutions GreenSeal 44	18	12	89 sq. ft.	ESR-3702		ER-0606
Profoam Proseal 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3835
Purinova Purios 500	4	3	400 sq. ft.	ESR-3702		ESR_4165
Purios 500	18	12	89 sq. ft.	ESR-3702		ESR-4165
Rhino Linings ThermalGuard 0.5 lb. OC	18	12	89 sq.ft.	ESR-3702	ER-0499	ESR-2100
Rhino Linings ThermalGuard 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-2100
Rhino Linings ThermalGuard 1 lb. OC	4	3	400 sq.ft.	ESR-3702		
Rhino Linings ThermalGuard 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-2100
Sealtite Pro Closed Cell	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0621
Sealtite Pro High Yield	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0623
Sealtite Pro No Trim 21	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0618
Sealtite Pro No-Mix	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0616
Sealtite Pro OCX	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0615
Sealtite Pro One Zero	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0640
Sealtite Pro Open Cell	14	9	New Spread Rate 115 sq. ft	ESR-3702	ER-0499	ER-0624
SES 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0374
SES 2.0 LE CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0374
SES Nexseal 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0374
SES Nexseal 2.0 LE	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0374
SES Spray Foam Insulation 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0492
SES Spray Foam Insulation 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0492
SES SucraSeal 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ESR-3375
Sopra SPF 202	18	12	89 sq. ft.	Update in Progress	Update in Progress	
Sopra SPF 202	18	12	89 sq. ft.	Update in Progress	Update in Progress	
Specialty Products, Inc. (S.P.I.) Envelope-Seal 0.5 lb.	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0656
Specialty Products, Inc. (S.P.I.) Envelope-Seal 2.0 lb. IBW CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0656
Spray Equipment & Coatings Spray EZ 2000 2 lb. CC	18	12	89 sq.ft.			
Spray Equipment & Coatings Spray EZ 500 0.5 lb. OC	20	13	80 sq.ft.			
Sustainable Polymer Products 0.5 lb. OC	14	9	115 sq. ft.	ESR-3702	ER-0499	ER-0513
Sustainable Polymer Products 0.5 lb. OC HY	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0514
Sustainable Polymer Products 0.5 lb. OCX	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0512
Sustainable Polymer Products 2 lb. CC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0511
Sustainable Polymer Products 2 lb. CC	14	9	115 sq. ft.	ESR-3702	ER-0499	
SWD QS100X 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft	ESR-3702	ER-0499	CCR-1050
SWD QS108 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	CCR-1051
SWD QS108 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCR-1051
SWD QuikShield 106 0.5 lb. OC	24	15	68 sq.ft.	ESR-3702	ER-0499	CCR-1011
SWD QuikShield 112 XC 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	CCR-1011
SWD QuikShield 118 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	Update in Progress	ER-0499	CCR-1093
The Spray Market SPM-200	18	12	89	ESR-3702	Update in Progress	ESR-4195
The Spray Market SPM-24K	4	3	400 sq. ft.	Update in Progress	Update in Progress	CCR-1084

Approved (SPF) Spray Foam Manufacturer and Type	Wet Film	Dry Film	Coverage Rate Per Gallon	IFTI ICC-ESR Evaluation report	IFTI IAPMO Evaluation report	SPF Manufacturer Evaluation report
The Spray Market SPM-24K	14	9	New Spread Rate 115 sq. ft	Update in Progress	Update in Progress	CCRR-1084
The Spray Market SPM-50M	4	3	400 sq. ft.	Update in Progress	Update in Progress	CCRR-1101
The Spray Market SPM-50M	18	12	89 sq. ft.	Update in Progress	Update in Progress	CCRR-1101
ThermoSeal 2000/2000W CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0581
Thermoseal CCX	18	12	89 Sq. Ft	ESR-3702	ER-0499	ESR-4137
Thermoseal OCX	18	12	89 Sq. Ft	ESR-3702	ER-0499	CCRR-1095
Thermoseal One	20	13	80 sq. ft.	ESR-3702		ER-0602
Thermoseal TS 360 OC	20	13	80 Sq. Ft.	ESR-3702	ER-0499	ER-0603
ThermoSeal TS 500 0.5 lb. OC	18	12	89 sq. ft.	ESR-3702	ER-0499	ER-0603
Thermoseal TS 800 0.8 pcf OC	20	13	80 sq. ft.	ESR-3702		ER-0603
TIGER FOAM® E-84 2 lb. CC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3183
UPC 500	6	4	267	ESR-3702		ESR-3803
UPC 500 OC 0.5 OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3803
UTC 7040 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-3244
UTC 7040 0.5 lb. OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3244
UTC 7041 0.5 lb. OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ESR-3244
UTC 7041 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ESR-3244
Versi-Foam® Class I 2 lb. CC	20	13	80 sq.ft.	ESR-3702		
Victory Polymers VPC Onestroke	4	3	400 sq. ft.	Update in Progress	ER-0499	ER-0599
Victory Polymers VPC- Onestroke	18	12	89 sq. ft.	Update in Progress	ER-0499	ER-0599
Volatile Free VFI-714 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0415
Volatile Free VFI-716 0.5 lb. OC	20	13	80 sq.ft.	ESR-3702	ER-0499	ER-0414
VPC-50 OC	14	9	New Spread Rate 115 sq. ft	Update in Progress	ER-0499	ER-0674
VPC-Superlift	18	12	89 sq. ft.	Update in Progress	ER-0499	ER-0655
VPC-Superyield	18	12	89 sq. ft.	Update in Progress	ER-0499	ER-0655
Xtremeseal 0.4 LX	4	3	400 sq. ft.	ESR-3702	Update in Progress	CCRR-1112
Xtremeseal 0.4 LX	14	9	New Spread Rate 115 sq. ft	ESR-3702	Update in Progress	CCRR-1112
Xtremeseal 2.0 LE 2 lb. CC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0537
Xtremeseal LX 0.5 lb. OC	14	9	New Spread Rate 115 sq.ft.	ESR-3702	ER-0499	ER-0538
Xtremeseal LX 0.5 lb. OC	4	3	400 sq.ft.	ESR-3702	ER-0499	ER-0538