



# THERMAX™ (ci) Exterior Insulation

## 1. PRODUCT NAME

THERMAX™ (ci) Exterior Insulation

## 2. MANUFACTURER

The Dow Chemical Company  
Dow Building Solutions  
200 Larkin Midland, MI 48674  
1-866-583-BLUE (2583)  
Fax 1-989-832-1465

www.thermaxwallssystem.com

## 3. PRODUCT DESCRIPTION

THERMAX™ (ci) Exterior Insulation consists of a glass-fiber-reinforced polyisocyanurate foam core faced with nominal 1.25 mil embossed BLUE™ thermoset-coated aluminum on one side and 0.9 mil smooth, reflective aluminum on the other. The integral durable thermoset coated aluminum facer provides a drainage plane and water resistive barrier, eliminating the extra step of installing a membrane or building wrap when used in conjunction with Dow Flashing products. The foam core provides one of the highest R-values<sup>(2)</sup> available (R-6.5 at 1") for immediate insulation and weather protection on the job site, as well as long-term thermal performance. THERMAX™ (ci) Exterior Insulation can remain uncovered up to six months. With its low perm rating and high insulating value, THERMAX™ (ci) Exterior Insulation can reduce the potential for condensation within the wall assembly.

With more than 30 years of exceptional performance, THERMAX™ products feature a distinct free-rise technology for better product consistency, durability and fire performance than generic polyisocyanurate insulations.

## Basic Use

THERMAX™ (ci) Exterior Insulation is designed for continuous insulation, which meets or exceeds ASHRAE 90.1-2013 prescriptive requirements for continuous insulation on exterior walls, as governed by building codes. The 1.25 mil embossed BLUE™ thermoset-coated aluminum surface makes it a durable exterior insulation choice.

## Sizes

See Table 1 for sizes, R-values and edge treatment options.

## 4. TECHNICAL DATA

### Applicable Standards

THERMAX™ (ci) Exterior Insulation meets ASTM C1289 – Standard Specification for Faced Rigid Cellular Polyisocyanurate Thermal Insulation Board, Type I, Class 2. Applicable standards include:

- C203 – Standard Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
- C209 – Standard Test Methods for Cellulosic Fiber Insulating Board
- C518 – Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- D1621 – Standard Test Method for Compressive Properties of Rigid Cellular Plastics
- D2126 – Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
- E96 – Standard Test Methods for Water Vapor Transmission of Materials
- D1623 – Standard Test Method for Tensile and Tensile Adhesion Properties

of Rigid Cellular Plastics

## Physical Properties

THERMAX™ (ci) Exterior Insulation exhibits the properties and characteristics indicated in Table 2 when tested as represented.

## Fire Protection

THERMAX™ products should be used only in strict accordance with product application instructions. THERMAX™ products, when used in a building containing combustible materials, may contribute to the spread of fire. For more information, consult (Material) Safety Data Sheet ((M)SDS) and/or call Dow at 1-866-583-BLUE (2583). In an emergency, call 1-989-636-4400.

## Code Compliances

THERMAX™ (ci) Exterior Insulation complies with the following codes:

- 2012 International Building Code (IBC) Section 2603
  - UL Classified; Class A UL 723 (ASTM E84) Surface Burning Characteristics of Building Materials
  - Fire Performance Evaluation approvals per NFPA 285, 2006 Edition (UBC 26.9, intermediate scale – multistory testing)
- ICC-ES ESR-1659
- FM DS 1-12 – Ceilings and Concealed Spaces, compliant as an FM approved Class 1 Foil-faced Polyisocyanurate Insulation in Cavity Walls
- FM 4880 – Factory Mutual Class 1 Insulated Wall and Ceiling Panel
- THERMAX™ products are covered under Underwriters Laboratories Inc. (UL) file R5622
- The following designs are 1, 2, 3 or 4 hour wall rated assemblies as listed in the UL Fire Resistance Directory: U026, U326, U330, U354, U355, U424, U425, U460, U902, U904, U905, U906, U907, V454, V482, V499, W417
- The following designs are 1, 2, 3 or 4 hour wall rated assemblies as listed in the Intertek Fire Resistance Directory: FI 60-02, FI 60-01, FI 120-01

Contact your Dow sales representative or local authorities for state and local building code requirements and related acceptances.

**TABLE 1: Sizes<sup>(1)</sup>, R-Values And Edge Treatments For Thermax™ (ci) Exterior Insulation**

Nominal Board Thickness (in.)	R-Value	Board Size (ft.)	Edge Treatment
0.625	4.1	4 x 8/4 x 12	Square Edge
1.0	6.5	4 x 8/4 x 12	Square Edge
1.55	10.1	4 x 8/4 x 12	Shiplap
2.0	13.0	4 x 8/4 x 12	Shiplap

<sup>(1)</sup> Contact your Dow seller for information at different R-values and other sizes and lead time requirements. Not all product sizes are available in all regions.

<sup>(2)</sup> Aged R-value at 1" of cured foam @ 75°F mean temperature. R-value expressed in ft 2 •h•°F/Btu. R-value determined by ASTM C518 using the aging process in ASTM C1289 (90 days @ 140°F).

## 5. INSTALLATION

Boards of THERMAX™ (ci) Exterior Insulation are lightweight and can be sawed or cut with a knife. They install quickly and easily to walls with common building tools. For optimum performance seal all joints between boards with LIQUIDARMOR-CM™ Sealant and Flashing or WEATHERMATE™ Flashing. Visit [www.building.dow.com](http://www.building.dow.com) to download the complete installation guide.

## 6. AVAILABILITY

THERMAX™ (ci) Exterior Insulation is distributed through an extensive network. For more information, call 1-800-232-2436.

## 7. WARRANTY

Fifteen-year limited thermal warranty as described in Form No. 179-00028.

## 8. MAINTENANCE

Not applicable.

## 9. TECHNICAL SERVICES

Dow can provide technical information to help address questions when using THERMAX™ (ci) Exterior Insulation. For technical assistance, call 1-866-583-BLUE (2583).

## 10. FILING SYSTEMS

[www.thermaxwallsystem.com](http://www.thermaxwallsystem.com)  
[www.dowbuildingsolutions.com](http://www.dowbuildingsolutions.com)

**TABLE 2: Physical Properties of THERMAX™ (ci) Exterior Insulation**

Property and Test Method	Value
Thermal Resistance <sup>(1)</sup> , ASTM C518, R-value	6.5
Compressive Strength <sup>(2)</sup> , ASTM D1621, psi	25.0
Flexural Strength, ASTM C203, psi	55.0
Water Absorption, ASTM C209, % by volume, max.	0.1
Water Vapor Permeance, ASTM E96, perms	≤0.04
Maximum Use Temperature, °F	250
Surface Burning Characteristics <sup>(3)</sup> , ASTM E84	
Flame Spread	25
Smoke Developed	<450

<sup>(1)</sup> Aged R-value at 1" of cured foam @ 75°F mean temperature. R-value expressed in ft<sup>2</sup>•h•°F/Btu. R-value determined by ASTM C518 using the aging process in ASTM C1289 (90 days @ 140°F).

<sup>(2)</sup> Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs first.

<sup>(3)</sup> Calculated flammability values for this or any other material are not intended to represent hazards that may be present under actual fire conditions.



In the United States

**The Dow Chemical Company**

**Dow Building Solutions**

200 Larkin Center

Midland, MI 48674

For Technical Information:

**1-866-583-BLUE** (2583) (English)

**1-800-363-6210** (French)

For Sales Information:

**1-800-232-2436** (English)

**1-800-565-1255** (French)

**[dowbuildingsolutions.com](http://dowbuildingsolutions.com)**

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries or regions. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted.

NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DOW. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Dow Polyisocyanurate Insulation

CAUTION: This product is combustible and shall only be used as specified by the local building code with respect to flame spread classification and to the use of a suitable thermal barrier. For more information, consult (Material) Safety Data Sheet (MMSDS), call Dow at 1-866-583-BLUE (2583) or contact your local building inspector. In an emergency, call 1-989-636-4400.8

WARNING: Rigid foam insulation does not constitute a working walkable surface or qualify as a fall protection product.

Building and/or construction practices unrelated to building materials could greatly affect moisture and the potential for mold formation. No material supplier including Dow can give assurance that mold will not develop in any specific system.

Printed in the U.S.A.

®/™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

Form No. 179-00015-0715 CDP