

THERMAX[™] SHEATHING

1. PRODUCT NAME THERMAX[™] Sheathing

2. MANUFACTURER

The Dow Chemical Company **Dow Building Solutions** 200 Larkin Midland, MI 48674 1-866-583-BLUE (2583) Fax 1-989-832-1465

www.dowbuildingsolutions.com

3. PRODUCT DESCRIPTION

THERMAX[™] Sheathing is a nonstructural, rigid board insulation consisting of a glass-fiber-infused polyisocyanurate foam core laminated between 1.0 mil smooth, reflective aluminum facers on both sides. The glass-fiber reinforcement contributes to improved fire performance and dimensional stability. THERMAX[™] Sheathing can be installed exposed to the interior without a thermal barrier.

THERMAX[™] Sheathing offers high, long-term R-value. Used in conjunction with the appropriate joint closure system for the application, THERMAX[™] Sheathing with its low perm rating helps to reduce moisture condensation within and behind the insulation.

BASIC USE

THERMAX[™] Sheathing is specially designed to have a Class A fire rating and can be used in a range of concealed and exposed applications, above and below grade, and can be used in exterior walls. Because of its improved fire performance, THERMAX™ Sheathing is especially appropriate for hourly rated assemblies. THERMAX[™] Sheathing is approved for use, per Section 2603.5 of the International Building Code, in Exterior Walls of Types I,II,III and IV construction. THERMAX™ Sheathing is designed for use as continuous insulation in both interior and exterior applications to assist in meeting and exceeding both the most current IECC and the ASHRAE 90.1 energy standards. Maximum

length is 30 ft. (9.1 m) and maximum thickness is 4.25" (108 mm) with R-value of 27.0.

4. TECHNICAL DATA

APPLICABLE STANDARDS

THERMAX[™] Sheathing meets ASTM C1289 - Standard Specification for Faced Rigid Cellular Polyisocyanurate Thermal Insulation Board, Type I, Class 2. Applicable standards include:

- C203 Standard Test Methods • for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
- C209 – Standard Test Methods for Cellulosic Fiber Insulating Board
- C518 Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- D1621 Standard Test Method for Compressive Properties of **Rigid Cellular Plastics**
- D2126 Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
- E96 Standard Test Method for • Water Vapor Transmission of Materials
- D1623 Standard Test Method for Tensile and Tensile Adhesion Properties of Rigid Cellular Plastics

TYPICAL PHYSICAL PROPERTIES

THERMAX[™] Sheathing exhibits the typical physical properties and characteristics indicated in Table 2 when tested as represented.

ENVIRONMENTAL DATA

THERMAX[™] Sheathing is manufactured with a zero ozone depleting potential. The use of THERMAX[™] Sheathing helps reduce the carbon footprint of commercial buildings.

FIRE PROTECTION

THERMAX[™] Sheathing products should be used only in strict accordance with product application instructions. THERMAX products

are combustible and when used in a building containing combustible materials, may contribute to the spread of fire. For more information, consult MSDS and/or call Dow at 1-866-583-BLUE (2583). In an emergency, call 1-989-636-4400.

CODE COMPLIANCES

THERMAX[™] Sheathing complies with the following codes:

- International Residential Code (IRC) Section 314
- International Building Code (IBC) Section 2603
- **ICC-ES NER-681**
- FM 4880 Wall-Ceiling Construction Metal-Faced - Class 1 Fire Rated to Max. 30' Exposure High, 4.25" Thick, 4' Wide, When Installed as Described in the Current Edition of FMRC Approval Guide
- THERMAX[™] products are classified by Underwriters Laboratories Inc. (UL)
- UL 1256 Fire Test of Roof Deck Constructions, Roof Deck Construction No. 120 and No. 123
- UL 723 (ASTM E84) Surface Burning Characteristics of **Building Materials**
- The following designs are 1, 2, 3 or 4 hour wall rated assemblies as listed in the UL Fire Resistance Directory: U026, U326, U330, U354, U355, U424, U460, U902, U904, U905, U906, U907, V454, V482
- Fire Performance Evaluation of ٠ an Exterior Masonry Wall System Incorporating THERMAX™ Insulation Tested in Accordance With NFPA 285, 2006 Edition (UBC 26.9, intermediate scale multistory testing)
- FMVSS No. 302 Flammability of Interior Materials - Passenger Cars, Multipurpose Passenger Vehicles, Trucks and Buses (Docket No. 3-3; Notice 4)
- Miami-Dade NOA 08-0320.01 Interior Insulation on CMU Block

Contact your Dow sales representative or local authorities for state and local building code requirements and related acceptances.

5. INSTALLATION

Boards of THERMAX[™] Sheathing are lightweight and can be sawed or cut with a knife. They install quickly to walls (girts, steel stud, tilt-up, block, wood) and ceilings – inside and outside of purlins, trusses or bar joints. Butt joints must be installed over structural members. "Best practice" recommendations for high-humidity environments include continuously sealing the surface of the insulation at all joints with a Dow joint closure system. Contact a local Dow representative or access the literature library at www.dowbuildingsolutions.com for more specific instructions.

6. AVAILABILITY

THERMAX[™] Sheathing is manufactured in several locations and is distributed through an extensive network. For more information, call 1-800-232-2436.

TABLE 1: SIZES, R-VALUES AND EDGE TREATMENTS FOR THERMAX[™] SHEATHING

NOMINAL BOARD THICKNESS ⁽¹⁾ , IN.	R-VALUE ⁽²⁾⁽³⁾	BOARD SIZE, FT	EDGE TREATMENT
.50	3.3	4 x 8, 4 x 9, 4 x 10	Square Edge
.75	5.0	4 x 8, 4 x 9, 4 x 10	Square Edge
1.0	6.5	4 x 8, 4 x 9, 4 x 10	Square Edge
1.25	8.1	4 x 8, 4 x 9, 4 x 10	Square Edge
1.5	9.8	4 x 8, 4 x 9, 4 x 10	Square Edge, Shiplap
1.55	10.1	4 x 8, 4 x 9, 4 x 10	Square Edge, Shiplap
1.75	11.4	4 x 8, 4 x 9, 4 x 10	Square Edge, Shiplap
2.0	13.0	4 x 8, 4 x 9, 4 x 10	Square Edge, Shiplap
2.5	15.8	4 x 8, 4 x 9, 4 x 10	Square Edge, Shiplap
3.0	19.0	4 x 8, 4 x 9, 4 x 10	Square Edge, Shiplap
3.5	22.1	4 x 8, 4 x 9, 4 x 10	Square Edge
4.0	25.2	4 x 8, 4 x 9, 4 x 10	Square Edge

(1) Not all product sizes are available in all regions.

(2) R means resistance to heat flow. The higher the R-value, the greater the insulating power. Stabilized R-values @ 75°F mean temperature determined in accordance with ASTM C518. R-values expressed in ft2•h•°F/Btu.

(3) An additional 2.77 R-value can be achieved with a 3/4" dead airspace when properly installed.

TABLE 2: TYPICAL PHYSICAL PROPERTIES OF THERMAX[™] SHEATHING

PROPERTY AND TEST METHOD	VALUE
Compressive Strength ⁽¹⁾ , ASTM D1621, psi, min.	25
Flexural Strength, ASTM C203, psi, min.	55
Dimensional Stability, ASTM D2126, % linear change, max.	0.1
Water Absorption, ASTM C209, % by volume, max.	0.05
Water Vapor Permeance, ASTM E96, perm, max.	<0.03
Maximum Use Temperature, °F	250

(1) Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs first.

www.dowbuildingsolutions.com

Technical Information 1-866-583-BLUE (2583) Sales Information 1-800-232-2436 IN THE U.S. THE DOW CHEMICAL COMPANY 200 Larkin Midland, MI 48674

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dow assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DOW. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

CAUTION: This product is combustible and shall only be used as specified by the local building code with respect to flame spread classification and to the use of a suitable thermal barrier. For more information, consult MSDS, call Dow at 1-866-583-BLUE (2583) or contact your local building inspector. In an emergency, call 1-989-636-4400.

WARNING: Rigid foam insulation does not constitute a working walkable surface or qualify as a fall protection product.

Building and/or construction practices unrelated to building materials could greatly affect moisture and the potential for mold formation. No material supplier including Dow can give assurance that mold will not develop in any specific system.



Form No. 179-04015X-0810MCk MCKAY20546



7. WARRANTY

Fifteen-year limited thermal warranty is available. Contact your Dow representative for details.

8. MAINTENANCE

Not applicable.

9. TECHNICAL SERVICES

Dow can provide technical information to help address questions when using THERMAX[™] Sheathing. Technical personnel are available to assist with any insulation project. For technical assistance, call 1-866-586-BLUE (2583).

10. FILING SYSTEMS

- www.dowbuildingsolutions.com
- www.sweets.com
- www.thermaxbydow.com