



FOAMSULATE™ 220

Spray Polyurethane Foam
2.0 pcf Density

TECHNICAL DATA

EQUIPMENT AND APPLICATION PARAMETERS:

Preheater Temperature "A" & "B" Side	125°F
Hose Temperature "A" & "B" Side	125°F
Mixing Ratio	1 to 1 By Volume Of "A" to "B"
Application Pressures	1,000 - 1,200 PSI
Ambient & Substrate Temperature - STANDARD APPLICATION	50°F - 120°F
Ambient & Substrate Temperature - COLD TEMPERATURE APPLICATION	Consult with PSP Technical Services for Cold Temperature (Winter) Application Guidelines.
Thickness Per Pass	Up to 3" Maximum

PRODUCT TYPE: Premium Spray Products, Inc. Foamsulate™ 220 is a two-component, medium density, one to one by volume spray applied polyurethane foam. To produce Foamsulate™ 220 requires the use of an "A" component (ISO) and a blended "B" component (RESIN) which contains ZERO Ozone Depleting blowing agents, catalysts, polyols and fire retarding materials.

GENERAL PROPERTIES: Foamsulate™ 220 is a nominal 2.0 pcf density closed cell insulating material. Foamsulate™ 220 is designed for use where insulation systems require superior air barrier characteristics along with the ability to minimize moisture infiltration. Foamsulate™ 220 has a 7.0 per inch R-value while providing structural enhancement due to its rigid nature when cured. When properly installed by a trained contractor Foamsulate™ 220 quickly expands to fill the cracks, crevices, gaps and voids that exist in every structure. In addition Foamsulate™ 220 will conform to the curves, irregular surfaces and spaces to form a superior thermal envelope around your entire structure.

RECOMMENDED USES: Foamsulate™ 220 is an insulation system designed for use in residential, commercial and industrial applications. Use in lieu of more traditional forms of insulating materials such as fiberglass, cellulose or other loose fill products. Typical areas where spray polyurethane foam is applied are; exterior walls, vented and un-vented attic assemblies, between floors, etc. Additional uses of this closed cell product are foundations, crawlspaces, HVAC ducts, fluid tanks, coolers, commercial building envelopes and as an air barrier.

THERMAL BARRIER: Current International Residential Code (IRC) and International Building Code (IBC) require that spray polyurethane foam be separated from the building interior by an approved 15-minute thermal barrier or a code approved alternative. Gypsum board at a minimum thickness of ½" is an approved 15-minute thermal barrier. The following intumescent coatings when installed per manufacturer specifications are approved as thermal barrier alternatives for Foamsulate 220: DC315™ manufactured by International Fireproof Technology, Inc. and Flame Seal-TB™ manufactured by Flame Seal Products, Inc.

IGNITION BARRIER: Foamsulate™ 220 meets the requirements of ICC-ES AC377 and Appendix X for use in attics and crawlspaces without the use of an ignition barrier.

EQUIPMENT AND APPLICATION PARAMETERS: The values represented in the Equipment and Application Properties Chart provides initial optimum settings. Actual operating ranges will vary as ambient air; humidity, moisture and substrate temperatures vary. Extreme conditions will affect the yield, adhesion and cured physical properties of the foam. Applicator must make adjustments as conditions vary.

STORAGE: Shelf life is six (6) months from date of manufacture when stored in original unopened containers between the temperatures of 65°F to 85°F.

SURFACE BURNING CHARACTERISTICS

Flammability	ASTM E 84 Class I At 4 Inches
Flame Spread < 20 Smoke Development < 450	

PRODUCT REACTIVITY

Product Designation	Temperature Range
Fast (20)	20°-50°F
Mid (50)	40°-65°F
Reg (80)	55°-80°F
Slow (100)	80°-100°F

CREDENTIALS CHART

Meets: NFPA 259, 285 and 286



Exterior Wall System Component In
Accordance With ANSI/NFPA 285.
See Buildings Materials Directory R38039.

PHYSICAL PROPERTIES

R-VALUE (Aged)	7.0 / Inch	ASTM C 518
Core Density	2.0 pcf	ASTM D 1622
Closed Cell Content	> 96%	ASTM D 1940
Sound Transmission Coefficient	38	ASTM E 413
Water Vapor Transmission - Permeance	1.49 Perms @ 1" .92 Perms @ 1.5"; .77 Perms @ 2"	ASTM E 96
Air Permeance	< 0.005L/sm ²	ASTM E 283
Noise Reduction Coefficient	0.10	ASTM C 423
Tensile Strength (PSI)	58	ASTM D 1623
Dimensional Stability	< .27	ASTM D 2126
Compressive Strength (PSI)	41	ASTM D 1621

The information herein is to assist customers in determining whether our products are suitable for their applications. Customer assumes full responsibility for quality control, testing, and determination of suitability of product for its intended use or application. Premium Spray Products, Inc. warrants only that the material shall meet its specifications; this warranty is in lieu of all other written, expressed or implied warranties and Premium Spray Products, Inc. expressly disclaims any warranty of merchantability, fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the material. Failure to adhere to any recommended procedures shall relieve Premium Spray Products, Inc. of all liability with respect to the material or the use thereof.

FOAMSULATE™ and Premium Spray Products are trademarks of Premium Spray Products, Inc.

FOAMSULATE™ 220

Spray Polyurethane Foam

2.0 pcf Density

For Professional Use Only

Experience the Premium Difference

General Information

Application Guidelines

Foamsulate™ 220 is suitable for application to most construction materials including: wood, masonry, concrete and metal. All surfaces to be sprayed with foam should be clean, dry and free of dew or frost. All metal to which the foam is to be applied must be free of oil, grease, etc. Three (3) inches should be the maximum thickness of each pass. Allow ten minutes between each pass to allow for cooling. Multiple layers can be applied to reach the desired thickness and R-value.

Substrate temperature at the time of the Foamsulate™ 220 application should be between 50°F to 120°F, the warmer the surface, the better the adhesion. When substrates to be sprayed are cooler than 50°F, a half inch pass should be applied to provide a thermal break. Follow with a second pass as soon as the original pass is no longer tacky to the touch. For surface temperatures in the range of 120°F to 180°F, the substrate to be sprayed should be 120°F or above at the time of spraying.

As with all spray polyurethane foam systems, improper application techniques should be avoided. Examples of improper techniques include, but are not limited to, excessive thickness of spray polyurethane foam, off ratio material and spraying into or under rising foam. Potential results of improperly installed spray polyurethane foam include: dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed foam must be removed and replaced with properly installed spray polyurethane foam. It is the responsibility of the applicator to thoroughly understand all equipment technical information and safe operating procedures that pertain to a spray polyurethane foam application.

When changing the "B" side (resin) to another type of spray polyurethane foam it is very important the supply hoses and pumps are completely drained. Mixing of dissimilar product types will have an adverse effect on the finished product.

Spray polyurethane foam insulation is combustible. High intensity heat sources such as welding or cutting torches must not be used in close proximity to any polyurethane foam.

Large masses of spray polyurethane foam should be removed to an outside safe area, cut into smaller pieces, and allowed to cool before discarding into a trash receptacle.

Foamsulate™ 220 is NOT designed for use as an exterior roofing product. Please contact Premium Spray Products, Inc. for information on our spray polyurethane roofing systems

Equipment and Component Ratios

Polyurethane foam systems should be processed through commercially available spray equipment designed for that purpose. Foamsulate™ 220

"A" side is connected to the isocyanate pump and the Foamsulate™ 220 "B" side is connected to the resin pump. The proportioning pump ratio is 1 to 1 by volume. The pre-heater initial setting should be 125°F. The initial hose temperature should be 125°F. Equipment must be capable of maintaining temperature settings.

Finished Foam Protection

The finished surface of the sprayed polyurethane foam should be protected from the adverse effects of direct exposure of ultraviolet light from the sun. This exposure will cause dusting and discoloration. Protective coatings designed for use with polyurethane foams are available from Premium Spray Products, Inc.

Safe Handling of Liquid Components

When removing bungs from containers use caution as contents may be under pressure. Loosen the small bung first to allow any built up gas escape before completely removing. The resin "B" component will froth at elevated temperatures. Avoid prolonged breathing of vapors. In case of chemical contact with eyes, flush with water for at least 15 minutes and get medical attention. For further information refer to the Center for Polyurethanes at www.spraypolyurethane.org.

Health and Safety

Due to the reactive nature of these components respiratory protection is mandatory. The vapors and liquid aerosols present during application and for a short period thereafter must be considered – and appropriate protective measures taken – to minimize potential risks from overexposure through inhalation, skin or eye contact. These protective measures include: adequate ventilation, safety training for installers and other workers, use of appropriate personal protective equipment and a medical surveillance program. It is imperative that the applicator read and become familiar with all available information on proper use and handling of spray polyurethane foam. Additional information is available at: spraypolyurethane.org, polyurethane.org, sprayfoam.com or by contacting the technical services department of Premium Spray Products, Inc.

Storage and Use of Chemicals

Cold chemicals can cause poor mixing, pump cavitations or other process problems due to higher viscosity at lower temperatures. Storage temperatures should be 65°F to 85°F for several days before use, and should not exceed 90°F. Do not store in direct sunlight. Keep drums tightly closed when not in use and under dry air or nitrogen pressure of 2-3 psi after they have been opened. Shelf life is six (6) months from date of manufacture when stored in original unopened containers at 65°F to 85°F. Store in a dry and well-ventilated area.

Your Local Authorized Contractor



1255 Kennestone Circle, #200 · Marietta, Georgia 30066

Phone: 770.528.9556

www.premiumspray.com